

MÉDIA DOS VALORES OBTIDOS EM AULA

ENSAIO DE TEMPERABILIDADE JOMINY

Aço	VALORES DE DUREZA																										
	DISTÂNCIA DA BASE TEMPERADA (pol)																										
	1/16	2/16	3/16	4/16	5/16	6/16	7/16	8/16	9/16	10/16	11/16	12/16	13/16	14/16	15/16	1	1/8	1/28	1/38	1/48	1/58	1/68	1/78	2	2/14	2	
1035	48,6	32,7	24,7	22,2	19,7	18,4																					
8620	50,1	49,3	47,8	34,6	29,8	28,7	27,6	26,6	25,9	24,3	23,2	22,1	21,3	21,2	20,9	20,8	19,1										
8640	58,3	58,1	57,8	56,6	55,6	54,5	51,1	49,2	46,0	42,7	41,3	39,1	38,0	36,0	34,7	33,8	32,1	31,4	31,0	30,0	29,4						
5140	51,9	51,8	49,2	45,6	45,5	39,9	36,0	32,3	30,3	29,2	29,1	26,0	25,7	24,3	23,7	22,1	21,4	20,1	18,7								
4340	59,0	58,6	58,5	57,3	57,2	56,9	56,8	56,1	56,0	55,8	55,7	55,3	55,0	54,9	54,8	54,0	53,0	53,0	53,0	53,8	52,7	52,5	52,1	52,0	52,0	52,0	52,0
1080	64,1	63,0	62,3	51,0	49,2	46,8	44,7	44,3	44,0	43,5	43,0	42,0	41,0	40,8	40,0	39,7	38,6	37,3	37,0	36,5	36,0	35,2	35,0	35,0	34,8	34,0	34,0