

Zeta Potential Report

v2.3



Malvern Instruments Ltd - © Copyright 2008

Sample Details

Sample Name: NE G8 1

SOP Name: mansettings.nano

General Notes: Duição 100:900

File Name: G5 NE.dts

Dispersant Name: Water

Record Number: 14

Dispersant RI: 1,330

Date and Time: sexta-feira, 25 de agosto de 2023...

Viscosity (cP): 0,8872

Dispersant Dielectric Constant: 78,5

System

Temperature (°C): 25,0

Zeta Runs: 10

Count Rate (kcps): 336,4

Measurement Position (mm): 2,00

Cell Description: Clear disposable zeta cell

Attenuator: 11

Results

	Mean (mV)	Area (%)	St Dev (mV)
Zeta Potential (mV): -0,530	Peak 1: 1,34	95,3	2,28
Zeta Deviation (mV): 8,69	Peak 2: -38,2	4,7	2,17
Conductivity (mS/cm): 0,118	Peak 3: 0,00	0,0	0,00

Result quality : [See result quality report](#)

